

## **S1113 Adhesive Tape**

DS-S1113-REV5-0909

**Characteristics:** Adhesive tape on rolls with release paper.

**Applications:** Used in combinations with CCS-DHEC and DHEC. Can be sold separately

in case leak detection wires have to be brought out when installing CCS-

DHEC or DHEC.

Included in groupment packaging of IPEC. Double wrap of sealing strip is

applied on the pipe before shrinking of IPEC.

The adhesive tape can also be used on top of a weld bead of a girth weld, underneath a shrinksleeve to fill up and smoothen rough irregularities

caused by welding 2 pipes together.

**Product description:** S1113-XXXxYYYxZZZ

XXX = Width in mm YYY = Thickness in mm ZZZ = Length in mm

Material properties: Typical Softening point: 150°C

Typical Shear strength @ 23°C : 30 N/cm<sup>2</sup> @ 50 mm/min Typical Peel strength @ 23°C : 30 N/cm @ 50 mm/min

**Dimensions:** Width: 30 mm, 40 mm, 50 mm

Thickness: 1 mm

Length per roll: 30000 mm

**Product printing &:** No printing.

**Labelling**: The box in which S1113 is packed, is bearing a label mentioning:

Covalence Description, Part Number, Lotnbr, Quantity, Spec. Code

**Hot climates:** In hot climates (>30°C) it is recommended to use the S1113 strips with a

plastic release liner. Ordering description: S1113-40X1X30000-PL(C4)

Ordering Info: S1113 rolls are packed in a box

S1113-	Quantity per box
30x1x30000(C5)	5
40x1x30000(C4)	4
50x1x30000(C3)	3



corrosion protection group www.berrycpg.com

The leading global partner in protecting the integrity of critical infrastructure.

Berry Plastics warrants that the product(s) represented within conform(s) to its/their chemical and physical description and is appropriate for the use as stated on the respective technical data sheet when used in compliance with Berry Plastics written instructions. Since many installation factors are beyond the control of Berry Plastics, the user is obligated to determine the suitability of the products for the intended use and assume all risks and liabilities in connection herewith. Berry Plastic liability is stated in the standard terms and conditions of sale. Berry Plastics makes no other warranty either expressed or implied. All information contained in the respective technical data sheet(s) should be used as a guide and is subject to change without notice. This document supersedes all previous revisions. Please see revision date on the right.

Local Distributor / Representative:

For contact details of local Distributors / Representatives Please visit www.berrycpg.com.

Headquarters Franklin, MA, USA

Tel: +1 508 918 1714 US Toll Free: +1 800 248 0149 Fax: +1 508 918 1910 CPG@berryplastics.com Houston, TX, USA

Tel: +1 713 676 0085 US Toll Free: +1 888 676 7202 Fax:+1 713 676 0086 CPGH@berryplastics.com Tijuana, Mexico

Tel USA +1 858 633 9797 Fax US: +1 858 633 9740 Tel Mexico: +52 664 647 4397 Fax Mexico: +52 664 607 9105 CPGTJ@berryplastics.com

Westerlo, Belgium Tel. +32 14 722500 Fax +32 14 722570 CPGE@berryplastics.com Baroda, India Tel: +91 2667 264721 Fax: +91 2667 264724 CPGIN@berryplastics.com